



FIX1DC-DECK CAULKING

Revision: 01/2012

Page 1 of 2

Technical Data:

Base	Hybrid Silane
Consistency	Stable Paste
Curing system	Moisture Cure
Paintability	Not Paintable
Skin Formation(*)	30 min (23°C & 75% R.H)
Cure Rate (*)	2-3mm/24Hrs (23°C & 75% R.H)
Hardness (Shore A)	37
Change In Volume	< 2%
Specific Gravity	1.30g/mL
Maximum Deformation	± 30%
Temperature Resistance (cured)	-40°C to 100°C
Elastic Modulus 100%	0.39 N/mm ² (DIN53504)
Tensile/Shear Strength	1.20 MPa (DIN53504)
Elongation At Break	300% (DIN53504)
Application Temperature:	From +5°C to 35°C

(*) Values may vary depending on environmental conditions

Product:

Fix1DC is a high quality single component adhesive sealant with a low viscosity, excellent adhesive properties designed for Teak and Synthetic Teak caulking.

Fix1DC is moisture curing and forms a permanent elastic product. It is chemically neutral, suitable for use in marine, transport and construction areas, where a strong flexible UV and soap resistant rubber bond is required.

Characteristics:

- Easy application
- High extrudability and good workability
- Ecological advantages, free from acids, isocyanates, solvents, Phthalates, halogens.
- Excellent sandability after full cure (3-5 Days for best results)
- Excellent mechanical properties
- Flexible elastic rubber – movement accommodation up to 30%
- No bubble formulation within the sealant
- UV stable and colour fast

- Fix1DC is Not Paintable,
- Withstands all climatic conditions and suitable for use where pH neutral soap cleaning will occur.
- Verified by NOHSC as non-hazardous and ROHS as compliant for health reasons.

Note on Paintability:

Paint, varnish and other coatings do not adhere to Fix1DC Deck Caulking. After sanding the deck including the caulking, be sure to thoroughly clean any surrounding surfaces that are to be painted with a good industrial alcohol cleaner to remove any contaminants that may cause "Fish Eye"! Test surfaces before painting.

Applications:

Fix1DC is suitable for the caulking of seams in real teak, most other timber types, cork and Synthetic Teak decking. Please consult our technical department for substrates outside the above.

Note: The contents contained in this documentation are the result of our experiments and our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the real number of possible applications which are out of our control we cannot accept any responsibility for the results obtained. In every case it is recommended to carry out preliminary experiments and compatibility tests.

Fixtech Pty Ltd. PO Box 568, Southport, Qld 4215. Tel: +61 (0)7 5530 1099. Fax: +61 (0)7 5530 1322

Email: info@fixtech.com.au

Web: www.fixtech.com.au



FIX1DC-DECK CAULKING

Packaging:

Colour – Black

Packaging – 600mL foil bag

Shelf life:

12 months Foil Bags from production date, in unopened packaging stored in a cool and dry storage with temperatures between +5°C and +25° (Maximum). Hotter storage will reduce shelf life significantly.

Surfaces:

State of Surface: Solid without cracks or fissures, clean, dry, free of dust, debris and free of any residue oils or release agents.

Sealing/Priming:

- For teak timber and other porous substrates we recommend Fixseal Epoxy Sealer/Primer timber sealer be applied after pre-wiping the surface down with clean acetone.
- For Synthetic decking no need for sealing/priming.

Compatibility tests are strongly recommended.

Joint Dimensions:

Minimal Width: 2mm (bonding)
5mm (joint)

Maximum Width: 10mm (bonding)
30mm (joint)

Minimum Depth: 5mm (joint)

Recommendation: width of joint = 2 x depth

Resistance to Chemicals:

Good resistance to fresh and salt water, pH neutral soaps, aliphatic solvents, mineral oils, grease.

Poor resistance to aromatic solvents, concentrated and diluted acids and chlorinated hydrogens.

Application:

Method: Manual or pneumatic caulking gun

Application temperature: +1°C to +30°C

Clean up tools: Use industrial alcohol cleaner immediately after application and before curing

Tooling: Mild pH neutral soapy solution diluted with fresh clean water applied and tooled before skin formation.

Repair with: Fix1DC

Health- and Safety Recommendation:

Apply the usual industrial hygiene. Wear gloves . Safety Glasses.

Remarks:

- Fix1DC may Not be overpainted
- Fix1DC can be applied to a wide variety of substrates. Due to the fact that the specific properties of substrates will differ we strongly recommend compatibility tests.
- Fix1DC **is not resistant** to strong alkalis or acids, concentrated acids, chlorine and bleach solutions, caustic solutions, and cleaners containing sodium hydroxide.
- For teak deck cleaning please refer to the teak deck cleaning guide in your catalogue or from our website www.fixtech.com.au or call our technical department.
Fixtech does not warrant damage caused to Fix1DC or any other Fixtech product through the mis-use of cleaners.

Warranty:

In relation to the sale of this product Fixtech Pty Ltd makes no warranty of suitability for any specific purpose. In lieu of all warranties expressed or implied, Fixtech Pty Ltd will at its discretion will replace goods to the invoiced value or refund the purchase price of any defective material. In no case or under any circumstances will Fixtech Pty Ltd be held liable for incidental or consequential damage.

Note: The contents contained in this documentation are the result of our experiments and our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the real number of possible applications which are out of our control we cannot accept any responsibility for the results obtained. In every case it is recommended to carry out preliminary experiments and compatibility tests.

Fixtech Pty Ltd, PO Box 568, Southport, Qld 4215. Tel: +61 (0)7 5530 1099. Fax: +61 (0)7 5530 1322

Email: info@fixtech.com.au

Web: www.fixtech.com.au